

Soft conformal coating, Curing by UV - Dual cure

PRODUCT DESCRIPTION


ABchimie836UV is a transparent single component conformal coating designed to protect printed circuit boards subjected to harsh environments. It has dual cure technology (UV - humidity) for crosslinking in the shadow areas.

ABchimie836UV is the third generation of dual cure conformal coating developed by ABchimie. This conformal coating shows the best dielectric properties in humid environment on the market (Log Ohm > 10,5, IPC CC 830, SIR according to IPC TM 650 2.6.3.4).

ABchimie836UV may be applied by selective coating machine which is the ideal way to apply.

ABchimie836UV is compliant with REACH and RoHS regulations. If you want a certificate, please contact us (info@abchimie.com).

FEATURES

- Excellent adhesion in harsh environments,
- Fluorescent under UV light to control of the layer of conformal coating deposit,
- Operating temperature range -65°C to + 150°C,
- Can be soldered through without fear of highly toxic gases being produced,
- Resistant to mould growth,
- Excellent dielectric properties,
- Very fast curing under UV exposure,
- Moisture cure for shadowed areas,
- No VOC,
- Floor space saving compared with solvent based,
- High speed process, increase of the productivity,
- Low viscosity for select coat machine (used on head SC200, SC280, SC300 and SC400),
-  **Pending approval UL94 V0 and UL746E**

APPLICATION

ABchimie836UV can be applied by brush, spray or selective coating machine:

Recommended thickness	30 – 130 microns
Spraying	30-90 microns
Selective coating machine (film coater)	90-130 microns

Minimum temperature of 16°C and minimum relative humidity of 50% are recommended for coating application. The relative humidity of at least 50% is recommended for the second polymerization mechanism.

Before applying the printed circuit board must be clean, dry and free of moisture. PCBs are humidity sensor, it is important to remove it before coating application. A stage in an oven for 4 hours at 80 ° C is usually sufficient.

The varnish ABchimie836UV contains a fluorescent tracer which permit to check good varnish deposit, inspection of PCBs and facilitate inspection. The higher the fluorescence level, the higher the coating thickness.

PREPARATION OF THE PCB

PCBs must be free of moisture and perfectly clean (no dust, grease, wax...). Adhesion of the coatings is depending on substrate quality. All traces of flux should be eliminated because they can become corrosive and create malfunction of the circuit.

CLEANING

To clean equipment or clean uncured varnish ABchimie836UV, we recommend using SND or DNS solvent.

CURING CONDITIONS

ABchimie836UV cures with UV rays and moisture for the second cure mechanism.

UV Curing :

It is important to use the appropriate UV equipment (UV or LED) as well as the recommended settings for the best properties of ABchimie836UV. These parameters have some effects on the reactivity and the surface of coating.


Recommended parameters :

Curing equipment : **arc lamp (mercury)**

Distance UV lamp – PCB : **1 to 10cm**

Minimum UVA dose: **1500mJ/cm²** (100µm)

Minimum UVA power: **150mW/cm²**




A slight residual tack due to the oxygen in the air can appear. It disappears a few minutes after passing under the lamp.

The UV dose given is a minimum to guarantee a good level of cure of varnish. A higher dose of UV or an overexposure will not damage the product.

Moisture cure:

Ambient temperature, 50% minimum relative moisture for 7 days

Curing mechanism :



PROPERTIES

ABchimie836UV liquid

Base	Urethane Acrylate
Appearance	Transparent yellow
Non-volatile residue	> 98%
Viscosity at 25 ° C	50 - 100 cSt
Flash point	> 100°C
Film Thickness	30 to 130 microns

ABchimie836UV cured

Appearance	Transparent
Adhesion ISO 2409	Class 0 (excellent)
Volume resistivity	10 ¹⁴ Ohm / cm
Insulation resistance (Ω)	10 ¹² (NF EN 61086)
Dielectric strength	60kV/mm
CTI (DIN EN 60112)	Pending
Tg	Pending
CTE (T < Tg)	Pending
CTE (T > Tg)	Pending
Insulation resistance in a humid environment	
SIR according to IPC TM 650 2.6.3.4	> 3,16 .10 ¹⁰ Ω
SIR according to IPC TM 650 2.6.3.3	> 1,5 .10 ⁹ Ω
BONO test	corrosion factor < 2 (coating alone)
Breakdown voltage	> 1500V AC
(according to IPC TM 650 2.5.7.1)	
Temperature range from	-65°C to + 150 °C



Varnish removal method

Mechanical (micro-abrasion)

Locally with chemical stripper (DVP)

Auto-extinguishing

Pending



PACKAGING:

ABchimie836UV

1 liter
5 liters

REFERENCES

ABchimie836UV 01L
ABchimie836UV 05L

PACKAGING:

Cleaner

Bulk 5 litres

REFERENCES

SND 05 L

STORAGE AND SHELF LIFE:

Storage temperature: 5 to 30°C

A temporary lower or higher (maximum 40°C) temperature during few days (transport) doesn't distort varnish properties.

ABchimie836UV must be stored in an opaque container, sealed away from excessive heat, at temperatures not exceeding 40 ° C. The varnish ABchimie836UV cures under UV action, it musn't be exposed to any light source.

This varnish also crosslinking with moisture, make sure there is no moisture in the deposition process and in cans open. After opening a bottle, it is recommended to purge these cans started with a dry inert gas (nitrogen) to prevent polymerization of the coating during storage.

Shelf life: 12 months after the date of manufacturing

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification. ABchimie cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.